


# Spiaggia Bianca


Limestone



## Formats

 Cut to Size & Custom Cuts, Slabs, Pavers, etc.

Featured: Spiaggia Bianca

Details	Test	Method	Results	
<p>Sizes: 40.60 x 61 x 3cm 30.50 x 61 x 1.2cm</p> <p>Pavers Sizes: 30.50 x 61 x 3cm 30.50 x 61 x 3cm with Bullnose 30.50 x 61 x 2cm 30.50 x 61 x 1.5cm</p> <p>Finish: Brushed</p>	Hardness	-	3-3.5 Mohs	
	Bulk Specific Gravity	Dry	TS EN 1936	2249 ± 14 kg/m <sup>3</sup>
		Saturated		2358 ± 10 kg/m <sup>3</sup>
	Density	TS EN 1936	2558 ± 21 kg/m <sup>3</sup>	
	Water Abs. at Atm. Press	By Volume	TS EN 13755	10.84 ± 0.36%
		By Weight		4.82 ± 0.19%
	Effective Porosity	TS EN 1936	10.84%	
	Real Porosity	TS EN 1936	12.08%	
	Fullness Ratio	TS 699	87.92%	
	Compressive Strength	TS EN 1926	44.8 ± 3.2 MPa	
Flexural Strength Under Concentrated Load	TS EN 12372	10.6 ± 0.8 MPa		
Flexural Strength Under Constant Moment	TS EN 13161	16.7 ± 1.2 MPa		
Impact Strength	TS 699	7.31 kg.cm/cm <sup>3</sup>		
Abrasion Strength (Method-B/Bohme)	TS EN 14157	23.6 ± 1.1 cm <sup>3</sup> / 50 cm <sup>2</sup>		
P-Wave Velocity	TS EN 14579	3866 ± 92 m/s		
<p><i>Color</i></p>  <p>Spiaggia Bianca</p>				
<p><i>Symbols</i></p> 