



TERRAZZO COLLECTION



# Azores

Distinguished • Elegant • Majestic  
Unique terrazzo engineered with the highest standards.

## Applications

Floors | Facades | Wall Cladding | Countertops

## Composition

Marble | Polyester Resin

## Available Finishes

Honed | Polished | Aged | Satin\*

Bush-Hammered\* | Sandy\*

\*0.79" thickness and up

Formats	Sizes	Thickness
Tile	11.8" x 11.8" (300 x 300mm)	0.47" (12mm)
	23.6" x 11.8" (600 x 300mm)	0.79" (20mm)
	23.6" x 23.6" (600 x 600mm)	
Slab	72" x 48.5" (1830 x 1230mm)	0.47" (12mm)
		0.79" (20mm)
		1.18" (30mm)

Minimum project quantities are required.

Please note that due to variances in quarried materials, final terrazzo color may differ slightly from this sample

Produced in Europe - Breton Technology



2701 E. State Highway 121, Bldg. 5, Suite 550,  
Lewisville, TX 75056

888.593.4441

[www.Dynamic-Stone.com](http://www.Dynamic-Stone.com)





TERRAZZO COLLECTION



**Azores**

---

Distinguished • Elegant • Majestic  
Unique terrazzo engineered with the highest standards.

Finishes	Polished	Honed	Aged	Satin	Bush-Hammered	Sandy
Interior	✓	✓	✓	✓	✓	✓
Exterior	X	✓	X	✓	✓	✓
Slip Resistance (Dry   Wet) PTV EN 14231	≤75   ≤10	≤67   ≤20	≤67   ≤15	≤70   ≤44	≤91   ≤81	≤64   ≤60

Technical Characteristics	Standard	Value	Class
Density	EN 14617-1	2515 - 2520 kg/m <sup>3</sup>	-
Water Absorption	EN 14617-1	0.02 - 0.03%	W2 <sup>(1)</sup>
Flexural Strength	EN 14617-2	28.7 - 30.7 MPa	F1/F2 <sup>(2)</sup>
Abrasion Resistance	EN 14617-4	≤33mm	A2 <sup>(3)</sup>
Mohs Hardness	EN 101	3 - 4 Mohs	-
Impact Resistance	EN14617-9	1.7 J (12mm) 2.4 J (20mm) 5.6 J (30mm)	-
Chemical Resistance	EN 14617-10	Acid < 60% alkali > 80%	C1 <sup>(4)</sup> C4 <sup>(4)</sup>
Reaction to Fire	EN 13501-1	-	A2 <sub>FL</sub> - S1 - d0
Freeze / Thaw Resistance	EN 14617-5	No visible defects KM <sub>f25</sub> + 0.87	-
Thermal Shock Resistance	EN 14617-6	No visible defects	-
Thermal Conductivity	EN 12664	2.175 W/m.K	-
Linear Thermal Expansion Coefficient	EN 14617-11	12.0 - 18.7 x 10 <sup>-6</sup> °C	-
Compressive Strength	EN 14617-15	120 - 150 MPa	-